



2540 - Black 2545 - White

PROTECTIVE COATING

For Commercial and Residential Use

A water based protective coating formulated with an EPA Registered preservative that prevents the growth of mold, mildew, and fungus on the surface of the coating. DP 2540 and DP 2545 form a durable, flexible film over metal, fiberglass insulation, drywall, and wood used in HVAC and general construction applications.

Recommended Uses:

- May be used to coat bare metal supply, return, and transfer HVAC duct.
- May be used to coat faced or unfaced fiberglass duct liner and rigid fiberglass duct.
- May be used to repair fiberglass insulation and effectively control fiberglass erosion.
- May be used to coat wood.

Features and Benefits:

- **LEED** Qualified
- Water Based
- Resists Mold and Mildew Growth on the Surface of the Coating itself (ASTM D-3273-00)
- Non-Flammable
- Smooth, Decorative Finish
- Encapsulates
- Flexible
- Durable

Directions For Use:

Surface Preparation: Surfaces should be clean, dry and free of dirt, oil, and any foreign matter. Surface should then be washed and sanitized with a high quality biocide and then thoroughly rinsed. Allow surfaces to completely dry. For painted surfaces, sand lightly to roughen substrate prior to cleaning.

Application: May be applied by brush, roller, or airless sprayer. Apply at a rate of 75 sq. ft. per gallon. Spray application should coat surface thoroughly and evenly with one application; apply second coat to porous or irregular surfaces. Brush or roller application requires two coats applied at 90 degrees. HVAC systems should be under negative air pressure during application. Circulate fresh air through the system to dry coating. Exhaust air should be odorless and filters replaced before venting into occupied areas.

Do not apply when rain or freezing temperatures will occur within 36 hours. Do not thin.

Technical Data:

Color: DP 2540-Black / DP 2545-White

Base: Water

Chemical Family: Synthetic Latex

Solids Content: 59 ± 2%

Viscosity: Approx. 4,000 - 5,000 cps

Application Temperature: 40°F - 110°F

Storage Temperature: 40°F - 110°F

Service Temperature: -25°F - 200°F

Freeze/Thaw Stability: Do not allow to freeze

Flammability: Non-flammable wet

Flash Point: No flash to boiling

Shelf Life: 1 Year (unopened containers)

Cure Time: 4-16 hours depending on humidity, temperature, and application

Clean Up: Use warm water and soap

Coverage on porous surfaces (insulation):

Approximately 75 sq. ft. per gallon

Coverage on non-porous surfaces (metal):

Approximately 400 sq. ft. per gallon

Packaging: 1 gallon pail, 5 gallon pail

VOC: 2 g/l

ASTM E-84 SURFACE BURNING CHARACTERISTICS
DP 2540/2545 Protective Coating applied to inorganic reinforced cement board
Flame Spread: 15 Smoke Developed: 10
Test applied at a spread rate of 200 sq. ft. per gal.
Flash point of finished coating, closed cup. No flash to boiling.

Revised 3-5-10



11609 Martens River Circle
Fountain Valley, CA 92708
Toll Free 800.641.0808
Phone 714.432.0600
Fax 714.432.0660
www.designpoly.com